

Torch Grade : HMW - HDPE Torch Grade

**HMW - HDPE
Burn-Off Film
0.36 MIL**

Nominal Thickness		0.36mil	
		(9 micron)	
Yield		80,655sq.in.per lb	
		560sq.ft.per lb	
Dart Impact		99.8g	ASTM D 1709
Tensile Strength at Break	MD	6300 psi	ASTM D 882
	TD	9981 psi	
Elongation at Break	MD	309%	ASTM 882
	TD	194%	
Elmendorf Tear	MD	16.2g	ASTM 1992
	TD	11g	
Coefficient of Friction	Static	0.282	ASTM D 1894
	Kinetic	0.244	
Melt Temperature		125 degrees C	

The above data are typical values only and should not be construed as a product specification.